

06X16H15M2Г2ТФР

also listed as 06Kh16N15M2G2TFR-ID


Chemical composition, mechanical and physical property values, and 5 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
5 in 1 regions	10 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Designations across standards

5 designations · 1 documented as identical

Russia / CIS	5
06Kh16N15M2G2TFR-ID This grade's own name	gost
06X16H15M2Г2ТФР	gost
06X16H15M2Г2ТФР-ИД	gost
ЧC68	gost
ЧC68-ИД	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 06X16H15M2Г2ТФР

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
—

ISSUED
Aug 15, 2026