

11860

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

OTHER DESIGNATIONS

1 in 1 regions

PROPERTY VALUES

6 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 99 % ● Si — 0.3 % ● Mn — 0.3 % ● Cu — 0.3 % ● Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

6 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	A5 %	Z %	HB
Bars hotrolled, GOST 11036-75	270	24	60	—
Bars cold-drawn , GOST 11036-75	350	4	—	—

CONDITION · DIMENSION	RM N/mm ²	A5 %	Z %	HB
Bars GOST 11036-75	—	—	—	131

Designations across standards

1 designations · 1 documented as identical

Russia / CIS	1
11860 This grade's own name	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 11860

[Start an enquiry](#)

Quotation, availability, mill certificate or a technical question — directly on the material page.

DATASHEET ONLINE

[View the material page](#)

GRADE SEARCH

[Search all grades](#)

MATERIAL NO.

—

ISSUED

Aug 15, 2026