

MATERIAL NUMBER 1.0028 · CLASS 1.0

16Д-Ш

Material no. 1.0028

also listed as S205G1T

Chemical composition, mechanical and physical property values, and 93 standard designations from 19 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 93 in 19 regions	PROPERTY VALUES 7 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Si, Ni, Cr, Mo.

Mechanical properties

6 values across 2 conditions

AS-DELIVERED STATE	RM N/mm ²	RE N/mm ²	A5 %
4 - 20	365–490	235	26

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %
Hot-rolled	330–430	165–205	21–28

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

93 designations · 3 documented as identical

United States15		United Kingdom10	
A284Gr.D	aisi-sae	1449-37/23CR	bs
A570Gr.33	aisi-sae	37/23HR	bs
A570Gr.33,36	aisi-sae	4360-40D	bs
A570Gr.36	aisi-sae	CEW2BK	bs
A573Gr.58	aisi-sae	Fe360B	bs
A611(A)	aisi-sae	Fe360D1FF	bs
A611Gr.C	aisi-sae	HFS4	bs
Gr.C	aisi-sae	HFW4	bs
K01804	aisi-sae	S235J2G3	bs
K02001	aisi-sae	S235JRG1	bs
K02301	aisi-sae		
K02502	aisi-sae	China8	
K02601	aisi-sae	A3	gb
K02701	aisi-sae	Q235	gb
K02702	aisi-sae	Q235A	gb
		Q235A-F	gb
		Q235A-Z	gb
Italy12		Q235B	gb
Fe330	uni	Q235B-F	gb
Fe360B	uni	Q235B-Z	gb
Fe360BFU	uni		
Fe360C	uni	France7	
Fe360CFN	uni	A34-2	afnor
Fe360D	uni	E24-3	afnor
Fe360DFF	uni	E24-4	afnor
Fe37-2	uni	S235J0	afnor
S235J0	uni	S235J2G3	afnor
S235J2G3	uni	S235J2G4	afnor
S235J2G4	uni	S235JRG1	afnor
S235JRG1	uni		

Spain7		Czechia3	
AE235B	une	11343	csn
AE235B-FU	une	11373	csn
AE235D	une	11378	csn
Fe360D1FF	une	Europe2	
S235J2G3	une	S205G1T	This grade's own name din-en
S235JR	une	Ust 34-2	This grade's own name din-en
S235JRG1	une	Japan2	
Russia / CIS6		SS330	jis
16D	gost	STKM12A	jis
16Д	gost	Poland2	
16Д-Ш	gost	St3SX	pn
18kp	gost	St3W	pn
18kn	gost	Austria2	
St3kp	gost	St34RG	onorm
Bulgaria5		St37TK	onorm
BSt3kp	bds	Belgium2	
Ew-08AA	bds	FE360B	nbn
S235J2G3	bds	FED1FF	nbn
S235JRG1	bds	Romania1	
WSt3kp	bds	OL37.4	stas
Hungary4		Finland1	
Fe235B/FU	msz	RACOLD215S	sfs
Fe235D	msz	South Korea1	
S235J2G3	msz	SS330	This grade's own name ks
S235JRG1	msz		
Sweden3			
1311	ss		
1312	ss		
1313	ss		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 16Д-Ш

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0028	Aug 20, 2026