

2X14H2

also listed as 25KH13N2

Chemical composition, mechanical and physical property values, and 4 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
4 in 1 regions	9 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 82.7 % Cr — 13 % Ni — 1.8 % Mn — 1 % Traces & impurities · 1.6 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

2 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	HB
Bar, GOST 18907-73	690–980	–
25KH13N2 (25X13H2) (annealing)	–	207–285

Physical properties

0 values

CONDITION · DIMENSION	RHO g/cm ³	ALPHA 10 ^{^-6} /K	LAMBDA W/(m·K)
20	7.68	–	18
100	–	11.6	19
200	–	12	20
300	–	12.4	22
400	–	12.8	24

Designations across standards

4 designations · 1 documented as identical

Russia / CIS	4
25KH13N2 This grade's own name	gost
25X13H2	gost
2X14H2	gost
ЭИ474	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 2X14H2

[Start an enquiry](#)

Quotation, availability, mill certificate or a technical question — directly on the material page.

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026