

MATERIAL NUMBER 1.5755 · CLASS 1.5

# 30Kh3VA

Material no. 1.5755

also listed as 31NiCr14

Chemical composition, mechanical and physical property values, and 18 standard designations from 10 regions.

|                              |                                               |                                      |
|------------------------------|-----------------------------------------------|--------------------------------------|
| DENSITY<br><b>7.85</b> g/cm³ | OTHER DESIGNATIONS<br><b>18</b> in 10 regions | PROPERTY VALUES<br><b>15</b> on file |
|------------------------------|-----------------------------------------------|--------------------------------------|

## Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 94.5 % ● Ni — 3.5 % ● Cr — 0.8 % ● Mn — 0.6 % ● Traces & impurities · 0.6 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

## Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

16 values across 3 conditions

| QUENCHING 850°C, OIL, DRAWING<br>200°C, AIR   | RM<br>N/mm <sup>2</sup> | RE<br>N/mm <sup>2</sup> | A5<br>% | Z<br>% | KCU<br>kJ/m <sup>2</sup> |
|-----------------------------------------------|-------------------------|-------------------------|---------|--------|--------------------------|
| Ø 5                                           | 1670                    | 1420                    | 13      | 50     | 660                      |
| Ø 20                                          | 1670                    | 1370                    | 12      | 45     | 490                      |
| QUENCHING 820°C, OIL, DRAWING<br>530°C, WATER | RM<br>N/mm <sup>2</sup> | RE<br>N/mm <sup>2</sup> | A5<br>% | Z<br>% | KCU<br>kJ/m <sup>2</sup> |
| Ø 25                                          | 980                     | 785                     | 10      | 50     | 780                      |
| CONDITION · DIMENSION                         |                         |                         |         |        | HB                       |
| (annealing) , GOST 4543-71                    |                         |                         |         |        | 241                      |

Physical properties

8 values

| CONDITION · DIMENSION    | RHO<br>g/cm <sup>3</sup> | E<br>GPa | ALPHA<br>10 <sup>-6</sup> /K | LAMBDA<br>W/(m·K) | CP<br>J/(kg·K)    | RHO_EL<br>nΩ·m |
|--------------------------|--------------------------|----------|------------------------------|-------------------|-------------------|----------------|
| 20                       | 7.85                     | 215      | —                            | 34                | —                 | 268            |
| 100                      | 7.83                     | 207      | 10.8                         | 35                | 494               | 317            |
| 200                      | 7.8                      | 195      | 11.5                         | 36                | 504               | 387            |
| 300                      | 7.77                     | 187      | 12.2                         | 36                | 518               | 469            |
| 400                      | 7.73                     | 175      | 12.8                         | 36                | 536               | 567            |
| 500                      | 7.7                      | 171      | 13.2                         | 35                | 558               | 681            |
| 600                      | 7.67                     | —        | 13.5                         | 31                | 587               | 817            |
| 700                      | 7.69                     | —        | —                            | 28                | 657               | 981            |
| 800                      | 7.65                     | —        | —                            | 27                | 703               | —              |
| 900                      | 7.6                      | —        | —                            | —                 | 695               | —              |
| 1000                     | —                        | —        | —                            | —                 | 687               | —              |
| PROPERTY                 |                          |          |                              | VALUE             | UNIT              |                |
| Density                  |                          |          |                              | 7.85              | g/cm <sup>3</sup> |                |
| Transformation point Ac1 |                          |          |                              | 700               | °C                |                |
| Transformation point Ac3 |                          |          |                              | 800               | °C                |                |
| Transformation point Ar3 |                          |          |                              | 680               | °C                |                |
| Transformation point Ar1 |                          |          |                              | 610               | °C                |                |

Technological properties

| PROPERTY           | VALUE                | UNIT |
|--------------------|----------------------|------|
| Weldability        | limited weldability. |      |
| Flake sensitivity  | predisposed          |      |
| Temper brittleness | predisposed          |      |

Designations across standards

18 designations · 1 documented as identical

|              |                       |        |                |  |      |
|--------------|-----------------------|--------|----------------|--|------|
| Russia / CIS |                       | 5      | United Kingdom |  | 1    |
| 30Kh3MA      | gost                  |        | 653M31         |  | bs   |
| 30Kh3VA      | gost                  |        |                |  |      |
| 30KHN3A      | gost                  |        | Spain          |  | 1    |
| 30X3BA-Ш     | gost                  |        | F.123          |  | une  |
| 30XH3A       | gost                  |        |                |  |      |
| France       |                       | 4      | Czechia        |  | 1    |
| 18NC13       | afnor                 |        | 16440          |  | csn  |
| 30NC11       | afnor                 |        |                |  |      |
| 30NC11FF     | afnor                 |        | Poland         |  | 1    |
| 30NC12       | afnor                 |        | 37HN3A         |  | pn   |
| Japan        |                       | 2      | Serbia         |  | 1    |
| SNC631       | jis                   |        | Č.5438         |  | srps |
| SNC836       | jis                   |        |                |  |      |
| Europe       |                       | 1      | Bulgaria       |  | 1    |
| 31NiCr14     | This grade's own name | din-en | 30ChN3A        |  | bds  |

**Note on use.** The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 30Kh3VA

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

|                        |                   |              |              |
|------------------------|-------------------|--------------|--------------|
| DATASHEET ONLINE       | GRADE SEARCH      | MATERIAL NO. | ISSUED       |
| View the material page | Search all grades | 1.5755       | Aug 20, 2026 |