

3X13H7C2

also listed as 30KH13N7S2

Chemical composition, mechanical and physical property values, and 4 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
4 in 1 regions	7 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 76.6 % Cr — 13 % Ni — 6.8 % Si — 2.5 % Traces & impurities · 1.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

5 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	Z %	KCU kJ/m ²
Bar, GOST 5949-75	1180	785	8	25	200

Designations across standards

4 designations · 1 documented as identical

Russia / CIS	4
30KH13N7S2 This grade's own name	gost
30X13H7C2	gost
3X13H7C2	gost
ЭИ72	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 3X13H7C2

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. —	ISSUED Aug 15, 2026
---	--	--------------------------	-------------------------------