

ДИ100-МП

also listed as R7M2F6-MP

Chemical composition, mechanical and physical property values, and 5 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
5 in 1 regions	8 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 91 % C — 3.4 % Si — 3.4 % Ni — 0.8 % Traces & impurities · 1.4 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

4 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	HB
Casting, GOST 7293-85	1000	700	2	—
GOST 7293-85	—	—	—	270–360

Designations across standards

5 designations · 1 documented as identical

Russia / CIS	5
R7M2F6-MP	gost
VCH100 This grade's own name	gost
BЧ100	gost
ДИ100-МП	gost
P7M2Φ6-МП	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about ДИ100-МП

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026