

3M962A

also listed as 16KH11N2V2MF

Chemical composition, mechanical and physical property values, and 4 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
4 in 1 regions	10 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 83.5 % ● Cr — 11 % ● W — 1.8 % ● Ni — 1.6 % ● Traces & impurities · 2.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Mechanical properties

5 values across 3 conditions

CONDITION · DIMENSION	RM N/mm ²	A5 %
Sheet thin, GOST 5582-75	830	22

CONDITION · DIMENSION	RM N/mm ²	A5 %
Sheet thin, GOST 5582-75	1320	10

CONDITION · DIMENSION	HB
16KH11N2V2MF (16X11H2B2MΦ) , Bar GOST 5949-75	285

Designations across standards

4 designations · 1 documented as identical

Russia / CIS	4
16KH11N2V2MF This grade's own name	gost
16X11H2B2MΦ	gost
2X12H2BMΦ	gost
3W962A	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 3W962A

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. —	ISSUED Aug 15, 2026
---	--	--------------------------	-------------------------------