

PK10Д3-6.4

also listed as PK10D3

Chemical composition, mechanical and physical property values, and 6 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
6 in 1 regions	2 on file


Chemical composition

Mass fraction in %



■ Iron — the balance, never listed by a standard — 97.2 % ■ Cu — 2.5 % ■ C — 0.3 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mn, Si, Ni, Cr, Mo.

Designations across standards

6 designations · 1 documented as identical

Russia / CIS	6
PK10D3 This grade's own name	gost
ПК10Д3	gost
ПК10Д3-6.0	gost
ПК10Д3-6.4	gost
ПК10Д3-6.8	gost
ПК10Д3-7.4	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about ПК10Д3-6.4
Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
—

ISSUED
Aug 15, 2026