

ПК10Н2Д2-6.8


also listed as PK10N2D2

Chemical composition, mechanical and physical property values, and 6 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
6 in 1 regions	3 on file

Chemical composition

Mass fraction in %



Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mn, Si, Cr, Mo.

Designations across standards

6 designations · 1 documented as identical

Russia / CIS	6
PK10N2D2 This grade's own name	gost
ПК10Н2Д2	gost
ПК10Н2Д2-6.4	gost
ПК10Н2Д2-6.8	gost
ПК10Н2Д2-7.2	gost
ПК10Н2Д2-7.6	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about ПК10Н2Д2-6.8
Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
—

ISSUED
Aug 15, 2026