

Sv-08KhN2M


also listed as 08G2S

Chemical composition, mechanical and physical property values, and 8 standard designations from 1 regions.


OTHER DESIGNATIONS	PROPERTY VALUES
8 in 1 regions	10 on file

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

3 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %
Ø 10 - 14	980	785	8

Physical properties

1 values

Technological properties

PROPERTY	VALUE	UNIT
Weldability	without limitations.	

Designations across standards

8 designations · 1 documented as identical

Russia / CIS	8
08G2S This grade's own name	gost
08Г2С	gost
Sv-08G2S	gost
Sv-08KhG2S	gost
Sv-08KhN2GMTA	gost
Sv-08KhN2GMYu	gost
Sv-08KhN2M	gost
ЭП-111	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Sv-08KhN2M

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026