

CE20BG2

also listed as 1518

Chemical composition, mechanical and physical property values, and 4 standard designations from 4 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
4 in 4 regions	8 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 98.2 % Mn — 1.4 % Si — 0.2 % C — 0.2 % Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

3 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %
25 – 25	≥ 1130	≥ 930	≥ 9

Heat treatment

2 regimes

STEP	TEMPERATURE	MEDIUM
source joins the operations with + / procedural order		
Quenching	860–890 °C	Water
Tempering	200–240 °C	—
source joins the operations with + / procedural order		
Quenching	860–900 °C	Water
Tempering	200–240 °C	—

Designations across standards

4 designations · 1 documented as identical

United States	1	Japan	1
1518	astm	SWRCHB620	jis
International	1	China	1
CE20BG2	iso	ML15MnB This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about CE20BG2

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026