

# FCD400-18A

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

## OTHER DESIGNATIONS

**1** in 1 regions

## PROPERTY VALUES

**0** on file

## Chemical composition

Mass fraction in %

No chemical composition is on file for this material number.

## Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: C, Mn, Si, Ni, Cr, Mo.

## Designations across standards

1 designations · 1 documented as identical

|                                               |     |
|-----------------------------------------------|-----|
| Japan                                         | 1   |
| FCD400-18A <span>This grade's own name</span> | jis |

**Note on use.** The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

## Enquiry about FCD400-18A

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

### DATASHEET ONLINE

View the material page

### GRADE SEARCH

Search all grades

### MATERIAL NO.

—

### ISSUED

Aug 20, 2026