

NCF600TB

Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
2 in 2 regions	9 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 10.3 % Ni — 72 % Cr — 15.5 % Mn — 1 % Traces & impurities · 1.2 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

7 values across 2 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %	HRB
Tubes Annealing	550	245	25–30	–
Annealed	–	–	–	92

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %
Tubes	550	245	30

Designations across standards

2 designations · 2 documented as identical

Japan	1	South Korea	1
NCF600TB This grade's own name	jis	NCF600TB This grade's own name	ks

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about NCF600TB

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. —	ISSUED Aug 20, 2026
---	--	--------------------------	-------------------------------