

MATERIAL NUMBER 1.0558 · CLASS 1.0

# 1.0558

Chemical composition, mechanical and physical property values, and 11 standard designations from 5 regions.

|                              |                                              |                                     |
|------------------------------|----------------------------------------------|-------------------------------------|
| DENSITY<br><b>7.85</b> g/cm³ | OTHER DESIGNATIONS<br><b>11</b> in 5 regions | PROPERTY VALUES<br><b>4</b> on file |
|------------------------------|----------------------------------------------|-------------------------------------|

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 99.9 % ● P — 0 % ● S — 0 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

## Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: C, Mn, Si, Ni, Cr, Mo.

Mechanical properties

10 values across 2 conditions

| NORMALIZING 860 - 880°C, DRAWING 600 - 630°C | RM<br>N/mm² | RE<br>N/mm² | A5<br>% | Z<br>% | KCU<br>kJ/m² |
|----------------------------------------------|-------------|-------------|---------|--------|--------------|
| to 100                                       | 569         | 334         | 11      | 20     | 245          |
| CONDITION · DIMENSION                        | RM<br>N/mm² | RE<br>N/mm² | A5<br>% | Z<br>% | KCU<br>kJ/m² |
| Casting, GOST 977-88                         | 736         | 392         | 14      | 20     | 294          |

Physical properties

2 values

| CONDITION · DIMENSION | RHO<br>g/cm³ | E<br>GPa | ALPHA<br>10^-6/K | LAMBDA<br>W/(m·K) | CP<br>J/(kg·K) | RHO_EL<br>nΩ·m |
|-----------------------|--------------|----------|------------------|-------------------|----------------|----------------|
| 20                    | 7.82         | 219      | –                | 48                | –              | 191            |
| 100                   | –            | 214      | 12               | 48                | 479            | 240            |
| 200                   | –            | 208      | 12.4             | 46                | 500            | 321            |
| 300                   | –            | 196      | 12.8             | 44                | 517            | 407            |
| 400                   | –            | 178      | 13.3             | 41                | 542            | 509            |
| 500                   | –            | 170      | 13.7             | 38                | 559            | 631            |
| 600                   | –            | 155      | 14.1             | 34                | 584            | 779            |
| 700                   | –            | 136      | 14.5             | 30                | 617            | 941            |
| 800                   | –            | 122      | 12.4             | 25                | 727            | 1139           |
| 900                   | –            | –        | 13.3             | 26                | 710            | 1170           |
| PROPERTY              |              |          |                  | VALUE             | UNIT           |                |
| Density               |              |          |                  | 7.85              | g/cm³          |                |

Technological properties

| PROPERTY    | VALUE                | UNIT |
|-------------|----------------------|------|
| Weldability | limited weldability. |      |

Designations across standards

11 designations · 3 documented as identical

| Europe     |                       |        | 3 | United States |                       |          | 2 |
|------------|-----------------------|--------|---|---------------|-----------------------|----------|---|
| GE 300     | This grade's own name | din-en |   | D50600        | This grade's own name | uns      |   |
| GS-60      | This grade's own name | din-en |   | A732(4A)      |                       | aisi-sae |   |
| GS-60N     |                       | din-en |   |               |                       |          |   |
| China      |                       |        | 3 | Russia / CIS  |                       |          | 2 |
| ZG310-570  |                       | gb     |   | 50L           |                       | gost     |   |
| ZG340-640  |                       | gb     |   | 50Л           |                       | gost     |   |
| ZGD345-570 |                       | gb     |   | Japan         |                       |          | 1 |
|            |                       |        |   | SCC5          |                       | jis      |   |

**Note on use.** The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

**Enquiry about 1.0558**  
Quotation, availability, mill certificate or a technical question — directly on the material page.

**Start an enquiry**

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0558

ISSUED

Aug 20, 2026