

MATERIAL NUMBER 1.0589 · CLASS 1.0

1.0589


Chemical composition, mechanical and physical property values, and 5 standard designations from 2 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 5 in 2 regions	PROPERTY VALUES 14 on file
--	---	--------------------------------------

Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 815 °C	PREDICTED AE1 711 °C	PREDICTED ACM 416 °C	PREDICTED BS 554 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

5 designations · 4 documented as identical

Europe	3	United States	2
GL-E 36	This grade's own name din-en	K11852	This grade's own name uns
GL-EH 36	This grade's own name din-en	K12437	uns
S355G3S	This grade's own name din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.0589

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0589

ISSUED

Aug 20, 2026