

MATERIAL NUMBER 1.0618 · CLASS 1.0

1.0618


Chemical composition, mechanical and physical property values, and 8 standard designations from 5 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 8 in 5 regions	PROPERTY VALUES 11 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

8 designations · 3 documented as identical

United States		4	United Kingdom		1
G10900	This grade's own name	uns	CS95		bs
G10950		uns			
1090	This grade's own name	aisi-sae	Japan		1
1095		aisi-sae	SK 4		jis
Europe		1	Brazil		1
C92D	This grade's own name	din-en	1095		abnt

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.0618

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0618	Aug 20, 2026