

MATERIAL NUMBER 1.0736 · CLASS 1.0

1.0736

Chemical composition, mechanical and physical property values, and 23 standard designations from 11 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 23 in 11 regions	PROPERTY VALUES 6 on file
--	---	-------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 98.1 % ● Mn — 1.3 % ● S — 0.4 % ● C — 0.1 % ● Traces & impurities · 0.2 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

11 values across 2 conditions

COLD DRAWN / HARD	RM N/mm ²	A %
5 – 10	510–810	6
10 – 16	490–760	7

COLD DRAWN / HARD	RM N/mm ²	A %
16 – 40	460–710	8
40 – 63	400–650	9
63 – 100	360–630	9
AS ROLLED AND TURNED		HB
As rolled and turned		107–169

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

23 designations · 6 documented as identical

United Kingdom	6	United States	2
1B	bs	G12150 This grade's own name	uns
230M07	bs	1215 This grade's own name	aisi-sae
240M07	bs		
240M07EN	bs	France	1
240M07EN 1B	bs	S300	afnor
EN1B	bs		
Europe	3	China	1
1.0736	din-en	Y13	gb
11 SMn 37 This grade's own name	din-en	Russia / CIS	1
9 SMn 36 This grade's own name	din-en	A12	gost
Spain	3	Italy	1
12SMn35	une	CF9SMn36	uni
F.2113	une		
F.2113-12 SMn 35	une	Latin America	1
Japan	3	1215	copant
12SMn35 This grade's own name	jis	South Korea	1
SUM23	jis	SUM25 This grade's own name	ks
SUM25	jis		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.0736

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

[View the material page](#)

GRADE SEARCH

[Search all grades](#)

MATERIAL NO.

1.0736

ISSUED

Aug 20, 2026