

MATERIAL NUMBER 1.1554 · CLASS 1.1

1.1554

Chemical composition, mechanical and physical property values, and 9 standard designations from 5 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 9 in 5 regions	PROPERTY VALUES 6 on file
--	---	-------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 98.5 % ● C — 1.1 % ● Mn — 0.2 % ● Si — 0.2 % ● Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

9 designations · 2 documented as identical

Czechia	3	Russia / CIS	2
19 XXX NN	csn	U12	gost
19221	csn	U12A	gost
19222	csn		
Europe	2	United States	1
C110U This grade's own name	din-en	W 1	aisi-sae
C110W This grade's own name	din-en	Serbia	1
		Č.1946	srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.1554

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.1554	Aug 20, 2026