

MATERIAL NUMBER 1.2834 · CLASS 1.2

1.2834


Chemical composition, mechanical and physical property values, and 7 standard designations from 5 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 7 in 5 regions	PROPERTY VALUES 7 on file
------------------------------	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

3 values across 2 conditions

CONDITION · DIMENSION	HB	HRC
Annealed	212	—
Quenched and tempered	—	63

SOFT ANNEALED	HB
Soft annealed	212

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

7 designations · 4 documented as identical

United States	3	Japan	1
T72302 This grade's own name	uns	SKS43	jis
W2 C 1,00% This grade's own name	aisi-sae	Czechia	1
W210 This grade's own name	aisi-sae	19356	csn
Europe	1	Slovakia	1
105V This grade's own name	din-en	19 356	stn

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.2834

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2834	Aug 20, 2026