

MATERIAL NUMBER 1.4021 · CLASS 1.4


1.4021

Chemical composition, mechanical and physical property values, and 56 standard designations from 17 regions.


DENSITY 7.7 g/cm ³	ELASTIC MODULUS 200 GPa	OTHER DESIGNATIONS 56 in 17 regions	PROPERTY VALUES 18 on file
---	-----------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

39 values across 9 conditions

CONDITION · DIMENSION	RM N/mm ²	A5 %	HB
Bar, GOST 18907-73	510–780	14	–

CONDITION · DIMENSION	RM N/mm ²	A5 %	HB
20KH13 (20X13) (annealing) , Bar GOST 5949-75	–	–	126–197
20KH13 (20X13) (normalize, tempering) , Bar GOST 18968-73	–	–	207–241
20KH13 (20X13) , Forging GOST 25054-81	–	–	197–248

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %	Z %	AK J/cm ²	HB	HRB	HV
Plate/Sheet Hot-rolled	520	225	18	–	–	–	–	–
Bars/Rods	640	440	20	50	78	–	–	–
Hot-rolled	–	–	–	–	–	223	97	234

SOFT ANNEALED	HB	HV
Soft annealed	230	190–240

QUENCHED AND TEMPERED	HV
Quenched and tempered	480–520

DRAWING 740 - 800°C	RM N/mm ²	A5 %
1 - 4	490	20

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	Z %	KCU kJ/m ²
Bar, GOST 5949-75	650–830	440–635	10–16	50–55	590–780

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	Z %	KCU kJ/m ²
Bar, GOST 18968-73	670	490–655	18	50	690

QUENCHING AND DRAWING	RM N/mm ²	RE N/mm ²	A5 %	Z %	KCU kJ/m ²
to 600	647	441	14–16	40–50	390–640

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %
Sheet trick, GOST 7350-77	510	375	20

Physical properties

12 values

CONDITION · DIMENSION	RHO g/cm ³	E GPa	ALPHA 10 ⁻⁶ /K	LAMBDA W/(m·K)	CP J/(kg·K)	RHO_EL nΩ·m
20	7.67	218	–	23	–	588

CONDITION · DIMENSION	RHO g/cm³	E GPa	ALPHA 10 ⁻⁶ /K	LAMBDA W/(m·K)	CP J/(kg·K)	RHO_EL nΩ·m
100	7.66	214	10.1	26	461	653
200	7.63	208	11.2	26	523	730
300	7.6	200	11.5	26	565	800
400	7.57	189	11.9	26	628	884
500	7.54	181	12.2	27	691	952
600	7.51	169	12.8	26	775	1022
700	7.48	–	12.8	26	963	1102
800	7.45	–	13	27	–	–
900	–	–	–	28	–	–

PROPERTY	VALUE	UNIT
Density	7.7	g/cm³
Elastic modulus	200	GPa
Thermal expansion coefficient	10.3	10 ⁻⁶ /K
Thermal conductivity	30	W/(m·K)
Specific heat capacity	460	J/(kg·K)
Electrical resistivity	600	nΩ·m
Transformation point Ac1	820	°C
Transformation point Ac3	950	°C
Transformation point Ar1	780	°C

Technological properties

PROPERTY	VALUE	UNIT
Weldability	limited weldability.	
Flake sensitivity	not predisposed	
Temper brittleness	predisposed	

Heat treatment

8 regimes

STEP	TEMPERATURE	MEDIUM
Annealing	Temperature not stated	—
Annealing	Temperature not stated	—

source joins the operations with + / procedural order

STEP	TEMPERATURE	MEDIUM
Quenching	Temperature not stated	—
Tempering	Temperature not stated	—
Quenching	Temperature not stated	—
Quenching	1000–1050 °C	Oil
source joins the operations with + / procedural order		
Quenching	Temperature not stated	—
Solution annealing	1000–1060 °C	—
Tempering	Temperature not stated	—
Ageing	600–700 °C	Oil
source joins the operations with (or)		
Annealing	Temperature not stated	—
Tempering	Temperature not stated	—
source joins the operations with + / procedural order		
Quenching	Temperature not stated	—
Solution annealing	Temperature not stated	—
Tempering	Temperature not stated	—
Ageing	Temperature not stated	—

Designations across standards

56 designations · 1 documented as identical

United States	14	Russia / CIS	11
S42000	uns	20Ch13	gost
420	aisi-sae	20KH13	gost
51420	aisi-sae	20X13	gost
S42000	aisi-sae	20X13	gost
S42010	aisi-sae	2X13	gost
A1049	astm	PK20Kh13	gost
A176	astm	Sv-20Kh13	gost
A182	astm	ПК20X13-6.4	gost
A276	astm	ПК20X13-6.8	gost
A314	astm	ПК20X13-7.4	gost
A473	astm	ст.20X13	gost
A580	astm		
F1079	astm	United Kingdom	4
F2215	astm	420 S 37 En56C	bs
		420S29	bs
		420S37	bs
		En56C	bs

France	4	China	2
X20Cr13	afnor	2Cr13	gb
Z20C13	afnor	X20Cr13	gb
Z20Cr13	afnor		
Z8CA12	afnor	Poland	2
Spain	4	2H13	pn
F.310.J	une	2H14	pn
F.3402	une	Italy	1
F.3402-X20Cr 13	une	X20Cr13	uni
X20Cr13	une		
Europe	3	Sweden	1
1.4021	din-en	2303	ss
S42010	din-en	Czechia	1
X20Cr13 This grade's own name	din-en	17022	csn
Japan	3	Slovakia	1
SUS 420J1	jis	17 022	stn
SUS 420J1FB	jis		
SUS 420J1TKA	jis	Brazil	1
United States / Aerospace	2	420	abnt
5506	ams	Serbia	1
5621	ams	Č.4172	srps
		former Yugoslavia	1
		Č.4172	jus

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.4021

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

[View the material page](#)

GRADE SEARCH

[Search all grades](#)

MATERIAL NO.

1.4021

ISSUED

Aug 20, 2026