

MATERIAL NUMBER 1.4321 · CLASS 1.4


1.4321

Chemical composition, mechanical and physical property values, and 12 standard designations from 8 regions.


DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 12 in 8 regions	PROPERTY VALUES 8 on file
--	--	-------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

12 designations · 1 documented as identical

France	3	Europe	1
Z3CAT18	afnor	X 2 NiCr 18 16	This grade's own name din-en
Z3CDFT18-02	afnor		
Z3CDT18-02	afnor	Spain	1
United States	2	F3123	une
S44401	uns	Japan	1
444	aisi-sae	SUS444	jis
China	2	Sweden	1
00Cr18Mo2	gb	2326	ss
019Cr19Mo2NbTi	gb	Romania	1
		2TiMoCr180	stas

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.4321

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4321	Aug 20, 2026