

MATERIAL NUMBER 1.4570 · CLASS 1.4

1.4570


Chemical composition, mechanical and physical property values, and 5 standard designations from 3 regions.

DENSITY 7.9 g/cm ³	OTHER DESIGNATIONS 5 in 3 regions	PROPERTY VALUES 11 on file
---	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Mechanical properties

1 values across 1 conditions

SOFT ANNEALED	HB
Soft annealed	215

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.9	g/cm³

Designations across standards

5 designations · 2 documented as identical

United States	3	Europe	1
S30330	uns	X6CrNiCuS18-9-2	This grade's own name din-en
S30331	This grade's own name uns		
303Cu	aisi-sae	Japan	1
		SUS303Cu	jis

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.4570

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.4570

ISSUED

Aug 20, 2026