

MATERIAL NUMBER 1.4659 · CLASS 1.4

1.4659


Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 2 in 2 regions	PROPERTY VALUES 12 on file
------------------------------	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no

transformation temperature is predicted here.

Mechanical properties1 values across 1 conditions

SOFT ANNEALED	HB
Soft annealed	290

Physical properties1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards2 designations · 2 documented as identical

Europe1	United States1
X1CrNiMoCuNW24-22-6This grade's own namedin-en	S31266This grade's own nameuns

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.4659

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4659	Aug 20, 2026