

MATERIAL NUMBER 1.5531 · CLASS 1.5

1.5531

Chemical composition, mechanical and physical property values, and 7 standard designations from 5 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 7 in 5 regions	PROPERTY VALUES 7 on file
------------------------------	---	-------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 97.9 % ● Mn — 1.3 % ● Si — 0.4 % ● C — 0.3 % ● Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

2 values across 1 conditions

QUENCHED AND TEMPERED · ROUND PRODUCTS	A % · Lo = 5,65 √So
≤ 16	13
16 – 40	13

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

7 designations · 1 documented as identical

United States	3	Russia / CIS	1
G13300	uns	30G2	gost
H1330	uns	Poland	1
1330	aisi-sae	30G2	pn
Europe	1	Romania	1
30MnB5 This grade's own name	din-en	T 30Mn14R	stas

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.5531

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.5531

ISSUED

Aug 20, 2026