

MATERIAL NUMBER 1.5918 · CLASS 1.5

1.5918


Chemical composition, mechanical and physical property values, and 5 standard designations from 4 regions.

DENSITY 7.77 g/cm ³	OTHER DESIGNATIONS 5 in 4 regions	PROPERTY VALUES 8 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

5 values across 5 conditions

TREATED TO IMPROVE SHEARABILITY	HB
Treated to improve shearability	255
SOFT ANNEALED	HB
Soft annealed	229
TREATED TO HARDNESS RANGE	HB
Treated to hardness range	175–229
TREATED TO FERRITE-PEARLITE STRUCTURE AND HARDNESS RANGE	HB
Treated to ferrite-pearlite structure and hardness range	156–207
CONDITION · DIMENSION	RM N/mm ²
200	1200

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.77	g/cm ³

Designations across standards

5 designations · 1 documented as identical

Europe	2	Poland	1
15CrNi6	din-en	15HN	pn
17CrNi6-6	din-en		
		Hungary	1
France	1	~BNC 5	msz
16NC6	afnor		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.5918

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.5918

ISSUED

Aug 20, 2026