

MATERIAL NUMBER 1.6369 · CLASS 1.6


1.6369

Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 2 in 2 regions	PROPERTY VALUES 14 on file
------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 806 °C	PREDICTED AE1 705 °C	PREDICTED ACM 407 °C	PREDICTED BS 539 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

2 designations · 2 documented as identical

Europe	1	United States	1
15NiCuMoNb5S This grade's own name	din-en	K21001 This grade's own name	uns

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.6369

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.6369	Aug 20, 2026