

MATERIAL NUMBER 1.6758 · CLASS 1.6


1.6758

Chemical composition, mechanical and physical property values, and 4 standard designations from 4 regions.


DENSITY 7.78 g/cm³	OTHER DESIGNATIONS 4 in 4 regions	PROPERTY VALUES 12 on file
------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 779 °C	PREDICTED AE1 707 °C	PREDICTED ACM 491 °C	PREDICTED BS 511 °C
--------------------------------	--------------------------------	--------------------------------	-------------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.78	g/cm³

Designations across standards

4 designations · 1 documented as identical

Europe	1	Poland	1
23MnNiMoCr5-4	This grade's own name din-en	23G2NMHA	pn
France	1	Romania	1
23MNCd5	afnor	24 MoCrNiMn 15z	stas

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.6758

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.6758

ISSUED

Aug 20, 2026