

MATERIAL NUMBER 1.8830 · CLASS 1.8

1.8830


Chemical composition, mechanical and physical property values, and 8 standard designations from 3 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 8 in 3 regions	PROPERTY VALUES 15 on file
------------------------------	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 818 °C	PREDICTED AE1 708 °C	PREDICTED ACM 385 °C	PREDICTED BS 542 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

8 designations · 2 documented as identical

Europe	4	United States	2
2YGr.60	din-en	2WGr.60	aisi-sae
S420G1	din-en	2YGr.60	aisi-sae
S420G1+M	This grade's own name din-en	Norway	2
S420G1+QT	This grade's own name din-en	Y35S420M3	ns
		Y35S420Q3	ns

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.8830

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.8830	Aug 20, 2026