

MATERIAL NUMBER 1.8900 · CLASS 1.8

1.8900


Chemical composition, mechanical and physical property values, and 7 standard designations from 5 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 7 in 5 regions	PROPERTY VALUES 15 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 803 °C	PREDICTED AE1 705 °C	PREDICTED ACM 436 °C	PREDICTED BS 537 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

7 designations · 2 documented as identical

Europe	3	United Kingdom	1
1.8900	din-en	4360 55 E	bs
S380N This grade's own name	din-en		
StE 380 This grade's own name	din-en	Italy	1
		FeE390KG	uni
United States	1		
A572-60	aisi-sae	Sweden	1
		2145	ss

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 1.8900

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.8900	Aug 20, 2026