SteelEquivalents.com

Material datasheet
As of Aug 20, 2026

MATERIAL NUMBER 2.4602 · CLASS 2.4

2.4602

Chemical composition, mechanical and physical property values, and 19 standard designations from 4 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
8.63 g/cm³	19 in 4 regions	13 on file

Chemical composition

Mass fraction in %

What this alloy is

Iron — the balance, never listed by a standard — 58.8 % · Cr — 21.3 % · Mo — 13.5 % · W — 3 % · Traces & impurities · 3.5 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	8.63	g/cm³

Designations across standards

19 designations · 3 documented as identical

United States 15

N06022 This grade's own name	uns
N26022 This grade's own name	uns
5388	aisi-sae
5388 C	aisi-sae
B 575	astm
B366	astm
B462	astm
B564	astm
B574	astm
B619	astm
B622	astm
B626	astm
B775	astm
B829	astm
B906	astm

China 2

H06022	gb
NS3308	gb

Europe 1

NiCr21Mo14W This grade's own name	din-en

France 1

NC 17 DWY	afnor

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 2.4602

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	2.4602	Aug 20, 2026