

MATERIAL NUMBER 1.0114 · CLASS 1.0

240 WC

Material no. 1.0114

also listed as S235J0


Chemical composition, mechanical and physical property values, and 30 standard designations from 21 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 30 in 21 regions	PROPERTY VALUES 10 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Si, Ni, Cr, Mo.

Mechanical properties

39 values across 3 conditions

FLAT AND LONG PRODUCTS	REH N/mm ²	RM N/mm ²		
≤ 3	–	360–510		
3 – 100	–	360–510		
≤ 16	235	–		
16 – 40	225	–		
40 – 63	215	–		
63 – 80	215	–		
80 – 100	215	–		
100 – 150	195	350–500		
150 – 250	–	340–490		
150 – 200	185	–		
200 – 250	175	–		
CONDITION · DIMENSION	A80 % · Lo = 80 mm	A % · Lo = 5,65 √So		
≤ 1	17	–		
1 – 1.5	18	–		
1.5 – 2	19	–		
2 – 2.5	20	–		
2.5 – 3	21	–		
3 – 40	–	26		
40 – 63	–	25		
63 – 100	–	24		
100 – 150	–	22		
150 – 250	–	21		
CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	Z %
Pipe, GOST 8696-74	372	245	23	–
Pipe, GOST 10705-80	372	225	22	–
Rolled stock, GOST 535-2005	370–490	205–255	23–26	–
Sheet trick, GOST 14637-89	370–480	205–245	23–26	–
Rebar, GOST 5781-82	373	235	25	–
Wire rods , GOST 30136-95	490–540	–	–	60

Physical properties

4 values

CONDITION · DIMENSION	RHO g/cm ³	
20	7.85	
PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Technological properties

PROPERTY	VALUE	UNIT
Weldability	without limitations.	
Flake sensitivity	not predisposed	
Temper brittleness	not predisposed	

Designations across standards

30 designations · 3 documented as identical

Europe	4	Spain	1
A284D	din-en	AE235C	une
Fe360C	din-en	International	1
S235J0 This grade's own name	din-en	E235C	iso
St 37-3 U This grade's own name	din-en	Norway	1
United States	3	NS12124	ns
K02401 This grade's own name	uns	Japan	1
A284C	aisi-sae	SM400B	jis
A284D	aisi-sae	Portugal	1
United Kingdom	2	FE360-C	np
40C	bs	China	1
Gr 40C	bs	Q235C	gb
Russia / CIS	2	Italy	1
St3ps	gost	Fe360C	uni
St3sp	gost	Sweden	1
Brazil	2	1312	ss
NBR 5008 CGR400	abnt	Czechia	1
NBR 5921 CFR400	abnt	11378	csn
Hungary	2	Slovakia	1
37 C	msz	11 378	stn
Fe 235 C	msz		
France	1		
E24-3	afnor		

Poland	1	Austria	1
St3W	pn	St360C	onorm
South Africa	1	Belgium	1
240 WC	sans	AE235C	nbn

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 240 WC

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
1.0114

ISSUED
Aug 20, 2026