

MATERIAL NUMBER 1.0345 · CLASS 1.0

Fe37BP

Material no. 1.0345

also listed as HI


Chemical composition, mechanical and physical property values, and 62 standard designations from 17 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 62 in 17 regions	PROPERTY VALUES 16 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 819 °C	PREDICTED AE1 717 °C	PREDICTED ACM 399 °C	PREDICTED BS 568 °C
-------------------------	-------------------------	-------------------------	------------------------

Mechanical properties

12 values across 1 conditions

AS-DELIVERED STATE	RM N/mm ²	RE N/mm ²	A5 %	KCU kJ/m ²
to 20	350–440	225	24	780
21 - 40	350–440	215	24	780
41 - 60	350–440	205	24	780

Physical properties

2 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Technological properties

PROPERTY	VALUE	UNIT
Weldability	without limitations.	

Designations across standards

62 designations · 11 documented as identical

United States		20	France		4
K01501	This grade's own name	uns	A37AP		afnor
K01700	This grade's own name	uns	A37CP		afnor
K02001		uns	AP		afnor
K02200	This grade's own name	uns	P235GH		afnor
K02201	This grade's own name	uns	Spain3		
K02202	This grade's own name	uns	A 37 RC Iune		
K02203	This grade's own name	uns	A37RCIune		
K02503	This grade's own name	uns	RA IIune		
K02601		uns			
K02801	This grade's own name	uns	Italy3		
-55		aisi-sae	Fe360-1KGuni		
55 A515 Gr.65		aisi-sae	Fe360-1KWuni		
A285		aisi-sae	FeE235uni		
A285Gr.C		aisi-sae	Czechia3		
A516		aisi-sae	11364csn		
A516Gr.65		aisi-sae	11366csn		
Gr.55		aisi-sae	11368csn		
Gr.65		aisi-sae	Russia / CIS2		
Gr.A		aisi-sae	12kgost		
A53-A	This grade's own name	astm	12Kgost		
Europe		6	Sweden2		
1.0345		din-en	1330ss		
A285Gr.C		din-en	1330-01ss		
ASt35		din-en	Belgium2		
HI	This grade's own name	din-en	D37-1.2nbn		
P235GH	This grade's own name	din-en	E37-1.2nbn		
StE255		din-en	International1		
United Kingdom		6	P3iso		
141-360		bs	China1		
1501		bs	20gb		
1501 Gr. 161-360		bs	Slovakia1		
161-360		bs	11 368stn		
161Gr.360		bs	Poland1		
400		bs	St36Kpn		
Japan		5	Austria1		
SB410		jis	St35KWonorm		
SGV410		jis			
SPV235		jis			
SPV24		jis			
SPV450		jis			

Finland	1
Fe37BP	sfs

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Fe37BP

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0345	Aug 20, 2026