SteelEquivalents.com

Material datasheet
As of Aug 20, 2026

MATERIAL NUMBER 1.5025 · CLASS 1.5

Č.2132

Material no. 1.5025

also listed as 51Si7

Chemical composition, mechanical and physical property values, and 9 standard designations from 5 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm³	9 in 5 regions	7 on file

Chemical composition

Mass fraction in %

What this alloy is

Iron — the balance, never listed by a standard — 97.1 % · Si — 1.7 % · Mn — 0.7 % · C — 0.5 % · Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

9 designations · 3 documented as identical

Poland 3

40S2	pn
50S2	pn
55S2	pn

United States 2

G92550 This grade's own name	uns
9255 This grade's own name	aisi-sae

Russia / CIS 2

40C2	gost
55C2	gost

Europe 1

51Si7 This grade's own name	din-en

Serbia 1

Č.2132	srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Č.2132

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
1.5025

ISSUED
Aug 20, 2026