

MATERIAL NUMBER 1.5860 · CLASS 1.5

Č.5427

Material no. 1.5860

also listed as 14NiCr18

Chemical composition, mechanical and physical property values, and 4 standard designations from 4 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 4 in 4 regions	PROPERTY VALUES 8 on file
--	---	-------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 93.4 % ● Ni — 4.5 % ● Cr — 1.1 % ● Mn — 0.6 % ● Traces & impurities · 0.5 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

4 designations · 1 documented as identical

Europe	1	Czechia	1
14NiCr18 This grade's own name	din-en	16523	csn
United States	1	Serbia	1
E 3316	aisi-sae	Č.5427	srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Č.5427

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.5860

ISSUED

Aug 20, 2026