

MATERIAL NUMBER 1.4818 · CLASS 1.4

2372

Material no. 1.4818

also listed as X6CrNiSiNce19-10


Chemical composition, mechanical and physical property values, and 4 standard designations from 3 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 4 in 3 regions	PROPERTY VALUES 10 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

1 values across 1 conditions

SOLUTION ANNEALED	HB
Solution annealed	210

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

4 designations · 2 documented as identical

United States		2	Europe		1
S30415	This grade's own name	uns	X6CrNiSiNce19-10	This grade's own name	din-en
S30415		aisi-sae			
			Sweden		1
			2372		ss

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 2372

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.4818

ISSUED

Aug 20, 2026