

MATERIAL NUMBER 1.7321 · CLASS 1.7

20MoCr5

Material no. 1.7321

also listed as 20MoCr4


Chemical composition, mechanical and physical property values, and 9 standard designations from 4 regions.

DENSITY 7.76 g/cm³	OTHER DESIGNATIONS 9 in 4 regions	PROPERTY VALUES 8 on file
------------------------------	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Mechanical properties

4 values across 4 conditions

TREATED TO IMPROVE SHEARABILITY	HB
Treated to improve shearability	255
SOFT ANNEALED	HB
Soft annealed	207
TREATED TO HARDNESS RANGE	HB
Treated to hardness range	156–207
TREATED TO FERRITE-PEARLITE STRUCTURE AND HARDNESS RANGE	HB
Treated to ferrite-pearlite structure and hardness range	140–187

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.76	g/cm ³

Heat treatment

8 regimes

STEP	TEMPERATURE	MEDIUM
Annealing	Temperature not stated	—
Spheroidize annealing	Temperature not stated	—
source joins the operations with + / procedural order		
Spheroidize annealing	Temperature not stated	—
Spheroidize annealing	Temperature not stated	—
Spheroidize annealing	Temperature not stated	—
Soft annealing	Temperature not stated	—
Soft annealing	Temperature not stated	—
Quenching and tempering	Temperature not stated	—
Soft annealing	Temperature not stated	—

Designations across standards

9 designations · 7 documented as identical

United States		6	Europe		1
G41180	This grade's own name	uns	20MoCr4	This grade's own name	din-en
H41180	This grade's own name	uns			
4118	This grade's own name	aisi-sae	Spain		1
4118H	This grade's own name	aisi-sae	20MoCr5		
4118RH	This grade's own name	aisi-sae			
EX4	This grade's own name	aisi-sae	Serbia		1
			Č.7420		srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 20MoCr5

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.7321	Aug 20, 2026