

MATERIAL NUMBER 1.4875 · CLASS 1.4

F.3214

Material no. 1.4875


also listed as X55CrMnNiN20-8

Chemical composition, mechanical and physical property values, and 6 standard designations from 4 regions.


DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 6 in 4 regions	PROPERTY VALUES 9 on file
------------------------------	---	-------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

1 values across 1 conditions

SOLUTION ANNEALED	HRC
Solution annealed	28

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

6 designations · 3 documented as identical

United States	3	United Kingdom	1
S63012 This grade's own name	uns	22-4-9	bs
EV 12 This grade's own name	aisi-sae	Spain	1
S63012	aisi-sae	F.3214	une
Europe	1		
X55CrMnNiN20-8 This grade's own name	din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about F.3214

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4875	Aug 20, 2026