

MATERIAL NUMBER 1.0760 · CLASS 1.0

CF35SMnPb

Material no. 1.0760

also listed as 38 SMn 28


Chemical composition, mechanical and physical property values, and 3 standard designations from 3 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 3 in 3 regions	PROPERTY VALUES 6 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

11 values across 2 conditions

COLD DRAWN / HARD	RM N/mm ²	A %
5 – 10	700–960	6

COLD DRAWN / HARD	RM N/mm ²	A %
10 – 16	660–930	6
16 – 40	610–900	7
40 – 63	600–840	7
63 – 100	580–820	8
AS ROLLED AND TURNED		HB
As rolled and turned		163–216

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

3 designations · 1 documented as identical

Europe	1	Italy	1
38 SMn 28 This grade's own name	din-en	CF35SMnPb	uni
France	1		
35MF4Pb	afnor		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about CF35SMnPb

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0760

ISSUED

Aug 20, 2026