

K02600

Chemical composition, mechanical and physical property values, and 4 standard designations from 2 regions.

OTHER DESIGNATIONS

4 in 2 regions

PROPERTY VALUES

0 on file

Chemical composition

Mass fraction in %

No chemical composition is on file for this material number.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: C, Mn, Si, Ni, Cr, Mo.

Designations across standards

4 designations · 2 documented as identical

United States		2	Canada		2
K02600	uns		300W	This grade's own name	csa
A36	astm		44W	This grade's own name	csa

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about K02600

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 13, 2026