

MATERIAL NUMBER 1.5425 · CLASS 1.5

K11123

Material no. 1.5425

also listed as 11MnMo4-5


Chemical composition, mechanical and physical property values, and 5 standard designations from 2 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 5 in 2 regions	PROPERTY VALUES 11 on file
------------------------------	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 821 °C	PREDICTED AE1 713 °C	PREDICTED ACM 377 °C	PREDICTED BS 557 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

5 designations · 5 documented as identical

United States		4	Europe		1
K11122	This grade's own name	uns	11MnMo4-5	This grade's own name	din-en
K11123	This grade's own name	uns			
K11222	This grade's own name	uns			
K11224	This grade's own name	uns			

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about K11123

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.5425	Aug 20, 2026