

MATERIAL NUMBER 1.4977 · CLASS 1.4

R30590

Material no. 1.4977

also listed as X 40 CoCrNi 20 20


Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 2 in 2 regions	PROPERTY VALUES 12 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

2 designations · 2 documented as identical

Europe	1	United States	1
X 40 CoCrNi 20 20 This grade's own name	din-en	R30590 This grade's own name	uns

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about R30590

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4977	Aug 20, 2026