

MATERIAL NUMBER 1.3346 · CLASS 1.3

T20841

Material no. 1.3346

also listed as HS2-9-1

Chemical composition, mechanical and physical property values, and 9 standard designations from 5 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
8 g/cm ³	9 in 5 regions	10 on file

Chemical composition

Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 82.9 % ● Mo — 8.6 % ● Cr — 3.9 % ● W — 1.8 % ● Traces & impurities · 2.9 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	8	g/cm ³

Designations across standards

9 designations · 6 documented as identical

United States		4	United Kingdom		1
T11301	This grade's own name	uns	BM1		bs
T20841	This grade's own name	uns			
H41	This grade's own name	aisi-sae	France		1
M1	This grade's own name	aisi-sae	Z85DCWV08-04-02-01		afnor
Europe		2	Serbia		1
HS2-9-1	This grade's own name	din-en	Č.7880		srps
S 2-9-1	This grade's own name	din-en			

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about T20841

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.3346	Aug 20, 2026